

## Termalene MP Extreme Pressure Grease

Termalene Multipurpose Extreme Pressure Grease, commonly known as Termalene EP Grease, is a severe duty, impact resistant, aluminum complex grease recommended for general lubrication service in both mining and industrial applications. Termalene Multipurpose Extreme Pressure Grease will replace most conventional and specialized products. Its low oil separation and good pumpability make it ideal for use in centralized lubrication systems and its Extreme Pressure protection and mechanical stability make it ideal for use in high load, high shear applications. Termalene Multipurpose Extreme Pressure Grease's water resistance and resistance to oxidation increase grease and bearing life.

### APPLICATIONS

- Typical mining applications are general lubrication on draglines and shovels, electric wheel motor sealing, anti-friction bearings, low- and high speed journal bearings, conveyors, shaker or classifier bearings, crusher bearings and most any heavy-duty application
- Typical industrial and mobile equipment applications are anti-friction bearings, low- and high speed journal bearings, general machinery lubrication, all chassis points including ball and universal joints, wheel bearings, king pins, fifth wheels and other severe duty applications

### PRODUCT FEATURES

- Mechanical stability
- High load capacity
- Water resistant

### BENEFITS

- Maintain consistency in high shear conditions and extends lubrication frequencies
- Impact resistance and superior retention properties
- Excellent lubrication in the presence of water and protection against rust
- Extends bearing life.

#### DISTRIBUTED BY:

Calumet Branded Products, LLC  
2780 Waterfront Pkwy. E. Dr., Suite 200  
Indianapolis, IN 46214  
Technical Services: 317-328-5660  
[www.belray.com](http://www.belray.com)

To the best of our knowledge, the information contained herein is accurate, but is given without warranty or guarantee. We assume no liability whatsoever for the accuracy or completeness of the information contained herein. Final determination of the suitability of any information or material for the use contemplated, the name of use and whether there is any infringement of patents is the sole responsibility of the user.

© 2020 Calumet Specialty Products, LLC. All Rights Reserved.

11/24/2021

# TECHNICAL DATA SHEET



Typical Physical Properties			
Property	Test Method	1	2
Worked Penetration	ASTM D217	325	280
NLGI Grade		1	2
Thickener Type		Aluminum Complex	Aluminum Complex
Viscosity @ 40°C, cSt	ASTM D445	220	180
Viscosity @ 100°C, cSt	ASTM D445	19.3	16.2
Dropping Point, °C (°F)	ASTM 2265	254 (490)	265 (509)
Oxidation Stability PD @ 100 hrs, kPa (psi)	ASTM D942	13.8 (2)	13.8 (2)
Water Washout %	ASTM D1264	1.3	0.5
4-Ball EP Test, Weld Load, kg	ASTM D2596	400	400
4-Ball EP Test, Load Wear Index	ASTM D2596	65.7	65.7
4-Ball Wear Scar Diameter, mm	ASTM D4172	0.45	0.42
Timken EP Test, OK Load, kg (lb)	ASTM D2509	22.8 (50)	22.8 (50)
Rust Protection	ASTM 1743	Pass	Pass
EMCOR Rust Protection	ASTM D6138	0, 0	0, 0
Useful Temperature Range, °C (°F)		-40 to 177 (-40 to 350)	-40 to 177 (-40 to 350)
Color		Red	Red

**DISTRIBUTED BY:**

Calumet Branded Products, LLC  
2780 Waterfront Pkwy. E. Dr., Suite 200  
Indianapolis, IN 46214  
Technical Services: 317-328-5660  
www.belray.com

To the best of our knowledge, the information contained herein is accurate, but is given without warranty or guarantee. We assume no liability whatsoever for the accuracy or completeness of the information contained herein. Final determination of the suitability of any information or material for the use contemplated, the name of use and whether there is any infringement of patents is the sole responsibility of the user.

© 2020 Calumet Specialty Products, LLC. All Rights Reserved.

11/24/2021